



# PRODUCT DATA SHEET

---

---

Effective Thickness

2.5 mm

(EN 1849-1)


---

## TECHNICAL INFORMATION

---

Tensile Strength	Max. Tensile strength longitudinal / transversal: 500 N / 50mm (± 20%) 400 N / 50mm (± 20%)	(EN 12311-1)
Elongation	Longitudinal / Transversal: 45% (± 15) 45% (± 15)	(EN 12311-1)
Tear Strength	150 N (± 30%) (nail shank)	(EN 12310-1)
Foldability at Low Temperature	-25°C	(EN 1109)
External Fire Performance	F roof (European Classification)	(EN 13501-5)
Reaction to Fire	F (European Classification)	(EN 13501-1)
Flow Resistance	To elevated temperatures: 100°C	(EN 1110)

---



tions the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, stor-

