



TECHNICAL DATA SHEET

SIKA SETTING SAND 20KG

Faster than traditional methods, Sika Setting Sand can be simply poured or swept into joints before being saturated with water giving perfect pointing for all types of block paving. Once cured it will not wash out, shrink or crack over time.

Buy SIKA SETTING SAND 20KG at

<https://www.spcsupplies.com/products/sika-setting-sand-20kg/>

SIKA - SPC SUPPLIES

[Waterproofing Supplies:](https://www.spcsupplies.com/shop/waterproofing/)

<https://www.spcsupplies.com/shop/waterproofing/>

[Admixtures and Building Chemical Supplies:](https://www.spcsupplies.com/shop/admixtures-and-building-chemicals/)

<https://www.spcsupplies.com/shop/admixtures-and-building-chemicals/>

[Flooring and wall finishing Supplies:](https://www.spcsupplies.com/shop/flooring-and-wall-finishing/)

<https://www.spcsupplies.com/shop/flooring-and-wall-finishing/>

[Adhesives, Sealants and Filler Supplies:](https://www.spcsupplies.com/shop/adhesives-sealants-and-fillers/)

<https://www.spcsupplies.com/shop/adhesives-sealants-and-fillers/>

[Wood Preservative Supplies:](https://www.spcsupplies.com/shop/wood-preservatives/)

<https://www.spcsupplies.com/shop/wood-preservatives/>

[Sika Concrete Repair Products and Concrete Protection Products:](https://www.spcsupplies.com/shop/concrete-repair-and-protection/)

<https://www.spcsupplies.com/shop/concrete-repair-and-protection/>

Partner Links:

[SD Sealants](https://www.sdsealants.co.uk/) - <https://www.sdsealants.co.uk/>

[Bettamix Concrete Manchester](http://www.bettamixconcretemanchester.co.uk) - <http://www.bettamixconcretemanchester.co.uk>

[Concrete Chemical Admixtures](http://www.concretechemicaladmixtures.com) - <http://www.concretechemicaladmixtures.com>

SIKA SETTING SAND



Colour	Product Code	Pack Size	Box Qty
Buff	SKSANDBF20	20 kg	

Product Description

Sika Setting Sand is an easy to use, moisture curing jointing material for all types of paving having joint width of 2 mm and over. Sika Setting Sand is suitable for all types of block paving and can be used in areas subject to light vehicular traffic.

Benefits

- Sets hard, wont crack or wash out.
- Resists weeds and insects.
- Suitable for all types of block paving.
- Weathers naturally in line with the paving.

Areas For Use

- Footpaths.
- Outdoor patio areas.
- Indoor stone floor areas.
- Pedestrian areas.
- Driveways.

Limitations

- Do not use on joints smaller than 2 mm wide. Joints that taper to a width less than 2 mm could result in failure.
- Joint depth must be a minimum of 25 mm
- Read all instructions carefully before use.
- Do not apply when rain is imminent or when temperature is 5°C or below.
- The jointing should not be cleaned by use of high pressure washers until cured for at least 28 days. The distance between nozzles and jointing must be at least 10 cm.
- Always follow the manufacturer's instructions carefully. As the company cannot be aware of all the applications and materials the product may be used on, it is the user's responsibility to determine suitability for use.
- Sika Setting Sand is unsuitable for long term use under water immersion although it will withstand typical wet/dry cycles.
- Ensure paved areas, beds and joints are well drained –ideally from beneath- to avoid standing water in joints over long periods.

Surface Preparation

Ensure that the paving to be jointed is dry and free from loose dirt, oil, debris and grease etc. it is essential the joint widths are a **minimum** of 2 mm wide with a **minimum** depth of 25 mm. Do not pre-fill joints with sand. Sika Setting Sand should be applied to the entire joint depth.

Application

It is recommended to carry out a small trial in an inconspicuous area or on off-cuts of paving prior to application.

Due to the nature of Sika Setting Sand, some settling of contents will occur. It is important to re-mix the dry material before use. Discard any small lumps and do not add extra sand to the dry material. Use in small, manageable amounts and avoid spreading over a large area. Sweep the material into the joints, making sure each joint is completely filled.

If rain is expected prior to hardening, the surface must be protected to ensure a smooth finish.

Sweep up any excess material immediately as it can be difficult to remove once set.

Thoroughly soak the joints with a hose pipe set to spray or a watering can fitted with a rose. Do not use a pressure washer.

Ensure joints are all fully saturated. Rinse excess material from the surface.

The finished surface is safe to walk upon immediately after activation, but ideally should be left to dry.

Drying will normally take 1 – 2 days although the time required for full cure is dependent upon temperature. At lower temperatures, the cure time will be slower. It will take up to 28 days to achieve full cure.

Clean tools immediately after use with warm soapy water.

Health & Safety

Consult MSDS for full list of hazards.

Storage

Store in a cool dry place at 5°C – 25°C. Protect packaging from punctures or piercings. Protect from frost. Do not keep on the ground. Do not store in direct sunlight.

Shelf Life

12 months from date of manufacture when stored in unopened containers in accordance with manufacturer's instructions.

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.